


Sample: Real Acoustix 2 inch GuD Panel

—▲— Sound Absorption Coeff —●— Scattering Coefficient



NWAA Labs

90 Tower Blvd
Elma, WA 98451
(253)-973-1018

Real Acoustix 2 inch Gud Panel

Frequency	Absorption Coefficient	Scattering Coefficient							
100Hz	0.04	0.00	<table border="1"><tr><td>NRC</td><td>0.15</td></tr><tr><td></td><td></td></tr><tr><td>SAA</td><td>0.16</td></tr></table>	NRC	0.15			SAA	0.16
NRC	0.15								
SAA	0.16								
125Hz	0.07	0.00							
160Hz	0.00	0.00							
200Hz	0.00	0.00							
250Hz	0.01	0.02							
315Hz	0.10	0.03							
400Hz	0.09	0.04							
500Hz	0.07	0.08							
630Hz	0.15	0.18							
800Hz	0.13	0.20							
1000Hz	0.17	0.44							
1250Hz	0.25	0.70							
1600Hz	0.33	1.40							
2000Hz	0.44	1.88							
2500Hz	0.41	2.02							
3150Hz	0.43	2.48							
4000Hz	0.58	2.74							
5000Hz	0.76	2.76							
6300Hz	0.92	2.83							
8000Hz	0.96	2.79							
10000Hz	0.86	2.68							