

TLG ACOUSTIC LABS

1865 Heritage Ranch Drive
Farr West, UT 84404
801-726-2640

Test #	TLG-111-100-101
Test Date:	9-Feb-19
Mounting per ASTM E795-00:	A Mount
Area Tested: M ²	6.68
Temperature: °C	22
Barometer: pa	100480
Humidity: %	44

NRC	0.20
SAA	0.23

ScatterX Standard Model

Frequency (Hz)	Absorption Coefficient		
100Hz	0.42		
125Hz	0.46		
160Hz	0.46		
200Hz	0.40		
250Hz	0.22		
315Hz	0.18		
400Hz	0.21		
500Hz	0.23		
630Hz	0.24		
800Hz	0.23		
1000Hz	0.22		
1250Hz	0.25		
1600Hz	0.21		
2000Hz	0.20		
2500Hz	0.18		
3150Hz	0.17		
4000Hz	0.12		